

ABL-SERIES

Component	Material		Weight(mg)	Substance	Weight(mg)	Weight(%)	
CAP	C7521R		164.83	Cu	112.096	19.09	
				Ni	31.527	5.37	
				Zn	20.493	3.49	
				Fe	0.280	0.05	
				Mn	0.438	0.07	
	PLATING	Ni	10.25	Ni	10.246	1.75	
ENCLOSURE	BASE	SPCC	310.40	Fe	300.684	51.22	
				P	5.587	0.95	
				S	3.414	0.58	
				Mn	0.559	0.10	
				C	0.124	0.02	
				Si	0.031	0.01	
	GLASS	FN-18AK	18.15	SiO ²	9.750	1.66	
				B2O3	1.500	0.26	
				AL2O3	1.500	0.26	
				Na2O3	1.500	0.26	
			K2O	1.500	0.26		
			Bis	0.900	0.15		
			BaO	0.750	0.13		
			ZnO	0.750	0.13		
TERMINAL	YEF29-17	58.91	Fe	30.669	5.22		
			Ni	16.847	2.87		
			Co	9.672	1.65		
			Mn	0.804	0.14		
			Si	0.402	0.07		
			Cu	0.402	0.07		
			Cr	0.115	0.02		
PIN	NSS	7.80	Cu	4.316	0.74		
			Ni	1.328	0.23		
			ETC	2.156	0.37		
Ni-EP	Ni	4.20	Ni	4.200	0.72		
Ni-ELP		3.00	Ni	2.760	0.47		
			P	0.240	0.04		
Sn-Cu		0.48	Sn	0.461	0.08		
			Cu	0.014	0.00		
BLANK	SiO2		5.04		5.040	0.86	
	ELECTRODE		0.08	Cr	0.002	0.00	
Ag				0.080	0.01		
BOND		THREEBOND 3301L	3.96	Ag	2.967	0.51	
				EPXY RESIN	0.989	0.17	
TOTAL			587.09			587.092	100.00